

Amendments to the Claims

Claims 1-6 (Cancelled).

Claim 7 (Previously presented): An aluminum alloy coating process for cast iron and steel products, consisting of:

preparing a surface of the product by jet-abrasion; and then

plunging the prepared product into an aluminum melt having a temperature of 660 – 680°C and

alloyed with zinc, silicon, magnesium and tin having mass percentages of:

zinc 7.0-10.0

silicon 3.0-5.0

magnesium 0.5-1.5

tin 0.2-0.5, and

for 70-80 seconds so as to coat the product with the alloy without the use of flux.

Claim 8 (Cancelled).